



PerformancePipe.com

DRISCOPEX® 8100

HDPE PIPE and FITTINGS DATA SHEET

DriscoPlex® 8100 Pipe and Fittings meet or exceed:

ASTM D2513, D2683, D3261
 ASTM D3350, cell classification PE445574C and PE445576C
 PPI TR-4 designation PE4710 (PE3408) and PE100
 PPI TN-30

DriscoPlex® 8100 Pipe and Fittings for:

Natural Gas Distribution, LPG and Propane Gas, Yard Gas
 Iron Pipe Size OD (IPS) ½" to 12",
 Copper Tube Size OD (CTS) ½" to 1 ¼"
 Coils available up through 6"
Outdoor Storage up to Three (3) years per ASTM D2513

NOMINAL PIPE PROPERTIES ⁽¹⁾	UNIT	TEST METHOD	VALUE
Density	gms / cm ³	ASTM D1505	0.961 (black)
Melt Index (MI) Condition 190°C / 2.16kg	gms / 10 minutes	ASTM D1238	0.08
Hydrostatic Design Basis 73° F (23° C)	psi	ASTM D2837	1600
Hydrostatic Design Basis 140° F (60° C)	psi	ASTM D2837	1000
Minimum Required Strength (MRS) @ 20° C (68° F)	Mpa (psi)	ISO 9080	>10 (>1450)
Rapid Crack Propagation Critical Pressure (Pc), 0°C (32°F) ⁽³⁾ Critical Temperature (Tc), 5 bar ⁽⁴⁾	Bar (psi) 0°C (°F)	ISO 13478 ISO 13477	>30 bar (>435 psi) <-24°C (<-11°F)
Color: UV Stabilizer [C] [E]		ASTM D3350	[C] Min 2% Carbon Black [E] UV Stabilizer, Yellow
Pipe Test Category	---	ASTM D2513	CEE
NOMINAL MATERIAL PROPERTIES	UNIT	TEST METHOD	VALUE
Flexural Modulus @ 2% Strain	psi	ASTM D790	>140,000
Tensile Strength at Yield	psi	ASTM D638 Type IV	>3500
Elongation at Break 2 in / min., Type IV Bar	%	ASTM D638	>800
Hardness	Shore D	ASTM D2240	65
PENT	hrs	ASTM F1473	>1000
Vicat Softening Temperature	°F	ASTM D1525	255
Brittleness Temperature	°F	ASTM D746	<-103
Thermal Expansion	in / in / °F	ASTM D696	1.0 x 10 ⁻⁴

- This is not a product specification and does not guarantee or establish specific minimum or maximum values or manufacturing tolerance for material or piping products to be supplied.
- Values obtained from tests of specimens taken from piping product may vary from these typical values.
- Determination made on 12" DR-11 pipes for Full Scale test. Pc calculated in accordance with ISO 13478.
- Determination made on 8" DR-11 pipes. No failures occurred. Tc calculated in accordance with ISO 13477 Annex C Correlation.

When Performance Matters Rely on
Performance Pipe

Bulletin: PP108

© 2009 Chevron Phillips Chemical Company LP

Performance Pipe, a division of Chevron Phillips Chemical Company LP | 5085 W. Park Blvd | Suite 500 | Plano, TX 75093 | Phone: 800-527-0662 | Fax: 972-599-7348

This data sheet provides typical properties for Performance Pipe DriscoPlex® pipe and fittings. Before using this product, the user is advised and cautioned to make their own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is application to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, allegedly arising from any usage of any trade or from any course of dealing in connection with the use of information contained herein or the product itself. The user expressly assumes all risk and liability.