

# High Density Polyethylene (HDPE) Electrofusion Fittings

## HDPE Electrofusion Reducers




HDPE Electrofusion Reducer Fittings are available to meet your needs in compliance with ASTM D2513, F1055, F2897, and where applicable, AWWA C906 product standards.

Electrofusion Fittings are manufactured from a PE 4710/PE100 resin as listed in PPI-TR4.

HDPE Electrofusion Fitting Material Physical Properties		
Property	Standard	Typical Value†
Material Designation	ASTM F412	PE4710
Cell Classification	ASTM D3350	445574C (black)
Density [4]	ASTM D4883	0.959 g/cc (black)
Flow Rate (HLMI, Condition 190/21.6)	ASTM D1238	8.0 g/10 min
Flexural Modulus [5]	ASTM D790	150,000 psi
Tensile Strength [5]	ASTM D638 Type IV	3625 psi
SCG (PENT) [7]	ASTM F1473	10,000 hours
HDB at 73°F (23°C) [4]	ASTM D2837	1600 psi
Color; UV stabilizer [C]	ASTM D3350	Black
Pressure Class (Gas)	49 CFR 192	125 psi
Pressure Class (Water)	AWWA C906	200 psi
Ambient Fusion Temperature	Manufacturer Specification	14°F-113°F

†This is not a product specification and does not guarantee or establish specific minimum or maximum values or manufacturing tolerance for material or piping products to be supplied. Values obtained from tests of specimens taken from piping product may vary from these typical values.

## HDPE Electrofusion Reducers



Electrofusion Reducer Size	Weight, lbs	Box Quantity	Part Number	Manufacturer Reference
1 CTS X 1/2 CTS	0.145	10	1120973	5911UU03010005
1" IPS X 1/2" CTS	0.136	10	1121354	5911BU03010005
1-1/4 IPS X 1-1/4 CTS	0.230	10	1120971	5911BU03013013
2" IPS X 1-1/4" CTS	0.626	4	1121355	5911BU03020013
2 IPS X 1-1/4 IPS	0.454	4	1120797	5911BB03020013
2 IPS X 2 CTS	0.620	4	1120972	5911BU03020020

Electrofusion Reducer Size	Dimensions L, inch	Dimensions A, inch	Dimensions A1, inch	Dimensions L1, inch	Dimensions L2, inch	Dimensions D, inch	Dimensions D1, inch	Ω @ 20°C, ohms	Fuse Time, sec	Fuse Volts	Cool Time, min
1 CTS X 1/2 CTS	3.15	1.61	1.61	1.53	1.38	1.77	1.30	2.10	30	40	10
1" IPS X 1/2" CTS	3.15	1.61	1.40	1.51	1.29	1.77	1.25	2.20	30	36	10
1-1/4 IPS X 1-1/4 CTS	3.53	1.85	1.85	1.77	1.77	2.18	2.18	2.05	60	40	10
2" IPS X 1-1/4" CTS	4.64	1.74	2.30	2.27	1.73	3.23	2.18	2.63	110	40	10
2 IPS X 1-1/4 IPS	4.64	2.24	1.93	2.27	1.85	3.22	2.2	2.30	90	40	10
2 IPS X 2 CTS	4.72	2.30	2.30	2.29	2.29	3.28	3.28	0.99	70	40	10

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.