

YELLOWSTRIPE® 8300

HDPE PIPE DATA SHEET

Yellowstripe® 8300 Pipe meets or exceeds:

ASTM D2513
ASTM D3350, cell classification PE445574C and PE445576C
PPI TR-4 designation PE4710 (PE3408) and PE100

Yellowstripe® 8300 Pipe for:

Natural Gas Distribution, LPG and
Propane Gas Distribution, Yard Gas
Iron Pipe Size OD (IPS) ½" to 24",
Copper Tube Size OD (CTS) ½" to 1 ¼"
Coils available up through 6"

Outdoor Storage up to Ten (10) years per ASTM D2513

NOMINAL PIPE PROPERTIES ⁽¹⁾		UNIT	TEST METHOD	VALUE
Density		gms / cm ³	ASTM D1505	0.961 (black)
Melt Index (HLMI)	190°C / 21.6 kg	gms / 10 minutes	ASTM D1238	9.0
Hydrostatic Design Basis	73° F (23° C)	psi	ASTM D2837	1600
Hydrostatic Design Basis	140° F (60° C)	psi	ASTM D2837	1000
Minimum Required Strength (MRS) @ 20°C (68°F)		Mpa (psi)	ISO 9080	>10 (>1450)
Rapid Crack Propagation Critical Pressure (Pc), 0°C (32°F) ⁽³⁾		Bar (psi)	ISO 13477	>12 bar (>174 psi)
Color: UV Stabilizer [C]		---	ASTM D3350	Min 2% Carbon Black
Pipe Test Category		---	ASTM D2513	CEE
NOMINAL MATERIAL PROPERTIES ^{(1) (2)}		UNIT	TEST METHOD	VALUE
Flexural Modulus @ 2% Strain		psi	ASTM D790	>150,000
Tensile Strength at Yield		psi	ASTM D638 Type IV	>3500
Elongation at Break 2 in / min., Type IV Bar		%	ASTM D638	>800
Hardness		Shore D	ASTM D2240	65
PENT		hrs	ASTM F1473	>2000
Vicat Softening Temperature		°F	ASTM D1525	255
Brittleness Temperature		°F	ASTM D746	<-103
Thermal Expansion		in / in / °F	ASTM D696	1.0 x 10 ⁻⁴

1. This is not a product specification and does not guarantee or establish specific minimum or maximum values or manufacturing tolerance for material or piping products to be supplied.
2. Values obtained from tests taken from actual piping product may vary from these typical values.
3. Determination made using Small-Scale Steady state. Pc calculated in accordance with ISO 13477.
4. Melt Index (MI) value determined in accordance with ASTM D3350 Cell Classification is <0.15 gm/10 min at 2.16kg.
5. Melt Index (MI) value determined in accordance with ASTM D3350 Cell Classification is <0.15 gm/10 min at 2.16kg condition.

When Performance Matters Rely on
Performance Pipe

Bulletin: PP109 / January 2012

© 2009 Chevron Phillips Chemical Company LP

Performance Pipe, a division of Chevron Phillips Chemical Company LP | 5085 W. Park Blvd | Suite 500 | Plano, TX 75093 | Phone: 800-527-0662 | Fax: 972-599-7348

This data sheet provides typical properties for Performance Pipe DriscoPlex® pipe and fittings. Before using this product, the user is advised and cautioned to make their own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, allegedly arising from any usage of any trade or from any course of dealing in connection with the use of information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user. The data sheet may change periodically. Visit www.PerformancePipe.com for the most current data sheet.